

MEGA FOAM POLYURETHANE FOAM

2 In 1 Expanding PU Foam

Technical Data Sheet

**PU FOAM & ADHESIVE RANGE****CLASS
DIN4102:1 B3**

Description:

A fast setting, multi-purpose PU foam which bonds, fills, seals and insulates most construction materials. Can be used as both gun grade or aerosol application.

Benefits:

- ◆ *Universal applicator valve - can be used at any angle.*
- ◆ *Can be used either as a gun grade version (Gunfoam Applicator- Pat. EP2004520, EE05028, RCD1635764) or as an aerosol version.*
- ◆ *High yield.*
- ◆ *Low curing pressure and moderate post expansion avoids deformation of building elements.*
- ◆ *High thermal and acoustic insulation value.*
- ◆ *Specially coated valve - problem free and will not corrode.*
- ◆ *Space saving as you only need to stock 1 can!*
- ◆ *Non-shrinking.*
- ◆ *B3 Rating according to DIN 4102-1.*

Bond It **MEGA FOAM** is a one-component polyurethane assembly foam, and is based on a moisture curing polyurethane prepolymer. Foam does not shrink after curing keeping the risk of deformation of joints and separation from the surface minimal.

Uses

The fresh foam adheres to all common building materials such as wood, concrete, stone, plaster, metal, PVC and polystyrene. however it will not stick to surfaces such as polyethylene, Teflon, silicone, oil and grease and similar substrates.

Areas of Application:

- ◆ installation of window and door frames and entrance door linings (where a clean and controlled backfill is required),
- ◆ filling of holes.
- ◆ insulation of penetrations.
- ◆ sealing of thermal and acoustic insulation boards.
- ◆ sealing and connection of joints.
- ◆ reducing the impact of thermal bridges.

Properties

The foam can be used at temperatures from +5°C to +30°C. The cured foam is semi-rigid and predominantly close-celled. It is resistant to temperatures ranging from -50°C to +90°C and to ageing, but not to UV-rays. Noise and heat insulation values are excellent.

Preparation

Surfaces to be bonded must be firm, clean, dry and free from dust, grease or contaminants that may hinder adhesion. They must be moistened well with water. All construction components must be properly prepared prior to foam application. It is advisable to have FOAM CLEANER at hand.

The ideal working temperature for both the can and environment is +20°C. Chilled cans must be carefully warmed in luke-warm water (below +45°C) before usage but avoid heating above +50°C, as there is a risk of bursting. Cans which are too hot, for example after having been left in a vehicle during summer, must be cooled using cold water. Protect adjacent surfaces with paper, plastic film or other suitable material. The can should be shaken occasionally during this process to obtain the required temperature faster.

Prior to work, and before the adaptor is attached, the can must be shaken thoroughly at least 15-20 times.

Application

As from 24 August 2023 adequate training is required before industrial or professional use.

The instructions for the can must strictly be observed. Use gloves and eye protection and avoid skin contact.

With Straw Adapter: Hold the foam can in upright position. Screw the applicator (straw) firmly to the foam can valve. For application, turn the can upside down and press the applicator trigger. Use the applicator trigger to adjust the foam output.

With Gun Adapter: Hold the foam can in upright position, turn the gun to the can by holding the gun handle with one hand, and turn the can with the other hand. Make sure that the gun is not pointed at other persons when turning it. The can must not be screwed to the gun with the valve upside down or by turning the gun on the can. Care must be taken not to overtighten the adaptor and not to activate the valve during this process. Turn the can upside down and start applying. The foam output can be adjusted by the gun trigger. Turn the can upside down and press the applicator trigger, using the trigger to adjust the foam output.

The fresh foam will expand by 1½ to 2 times. Therefore care must be taken not to overfill joints. Fresh foam spills must be removed

immediately within the tack-free time with Bond It FOAM CLEANER. Cured foam must be removed mechanically.

Please Note: Moisture is needed for an even and rapid curing of the foam. Inadequate moistening or overfilling of joints and cavities may lead to an unwanted post-expansion of the foam. Foam extrusion can be controlled accurately by varying the pressure on the adaptor or gun trigger. For foam extrusion the valve is pointed down but it will work through most angles. The valve lever is to be activated carefully. Once a can has been started, it should be used within four weeks.

Limitations

Cured foam is sensitive to UV light and direct sunlight and therefore should be covered with suitable opaque sealant, filler, paint or other material.

Cleaning

Excess foam can be removed whilst still wet using Bond It GUN FOAM CLEANER or Bond It MULTI-WIPES. Cured foam can only be removed mechanically.



Container Size

500ml and 750ml aerosol canisters.

Shelf Life

18 months from date of manufacture when stored according to manufacturers instructions in original unopened containers.

Storage Conditions

Store and transport upright, in cool, dry conditions between 5 and +30°C. (Considerably higher temperatures may reduce the shelf life). Do not store at temperatures over +50°C. Keep away from sources of heat and direct sunlight.

Disposal of Containers

Do not leave empty containers where residue could be harmful to children, animals or the environment. Replace lids and remove any containers to a central disposal point in accordance with local regulations. Do not pierce can. In the event of spillage remove all sources of ignition, ventilate the area, remove people from confined areas. Material should be mopped up immediately with an inert absorbent material such as sand, collected and placed in a suitable container or allowed to vaporise.

Health & Safety

Extremely flammable aerosol. Please refer to separate material safety data sheet for full handling, use and storage instructions. Keep out of reach of children. It contains an environmentally safe propellant, which complies to the latest EU regulations banning all CFC-propellants. It is the users responsibility to determine suitability for use. If in doubt contact our Technical Department for advice.

Note: this information is for general guidance only, since site conditions and labour are beyond our control. It is recommended that users make their own tests to determine suitability.

Specification Summary

Tack-Free (TM 1014)	6-10 minutes
Cutting Time	<30 minutes
Full Cure (Joint 3x5cm @ 23°C)	<8 hours
Curing Pressure (TM 1009, moistened surfaces)	<1kPa
Post Expansion (TM 1010)	<80%
Density In Joint (3x10cm; WGM106)	15-19Kg/m ³
Dimensional Stability (TM 1004)	<1%
Temperature Resistance of Cured Foam	-50°C to +90°C
Working Temperature (Can, application surfaces)	+5°C to +30°C
Tensile Strength/Elongation (TM 1018, dry surfaces)	>80kPa/ 22%
Tensile Strength/Elongation (TM 1018, moist surfaces)	>60kPa/ 22%
Compressive Strength (TM 1011 moistened surfaces)	>5kPa
Shear Strength (TM 1012 moistened surfaces)	>20kPa
Thermal Conductivity (EN12667, TM 1020)	0.033W/(m K)
Sound Reduction Index R _{st,w} (EN ISO 10140)	62dB
Water Vapour Permeability (EN 12086)	<0.06 mg/(m h Pa)
UN Class	1950 Aerosols, Flammable
UFI	

The values specified were obtained at +23°C and 50% RH, unless otherwise specified. These values may vary depending on environmental factors such as temperature, moisture and type of substrate.

Product / Order Details:

Code	Colour	Size	Barcode
BDEF500	Beige	500ml	5060021360731
BDEF750	Beige	750ml	5060021360748



Part of the Bond It PU Foams & Adhesives Range



The data presented in this leaflet are in accordance with the present state of our knowledge, but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this leaflet should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies raw materials are also being used. The recommendations do not absolve the user from the obligation of investigating the possibility of infringement of third parties rights and, if necessary clarifying the position. Recommendations for use do not constitute a warranty, either expressed or implied, of the fitness or suitability of the products for a particular purpose.



Certificate Number:
6152
ISO 9001; ISO 14001;
ISO 45001



BOND IT
Head Office: Unit G16 River Bank Way, Lowfields Business Park,
 Elland, West Yorkshire HX5 9DN.
 Telephone: +44 (0)1422 315300 Fax +44 (0)1422 315310
 Email: salesuk@bonditgroup.com Website: www.bonditgroup.com



Rev: V6 10/10/21
 Supersedes: V5 20/10/21