

PRODUCT DATA SHEET

EVERBUILD® BLACK JACK® 908 D.P.M.

Ready to use, effective damp proof membrane.

PRODUCT DESCRIPTION

EVERBUILD® BLACK JACK® 908 D.P.M. is a rubber enriched bitumen emulsion which provides a highly effective sandwich damp proof membrane for floors. Also acts as a waterproofer for walls, above ground structures and foundations. DPM is also suitable as an adhesive for wood block and mosaic panels, insulation boards, expanded polystyrene, cork and as a plaster bonding agent, even on difficult surfaces.

USES

Commonly used in the following areas:

- Providing sandwich damp-proof membranes for floors.
- General waterproofing: - for use on concrete, fibre/cement, render, plaster etc.
- For waterproofing structures such as bridge abutments, retaining walls and culverts.
- For fixing wood blocks and wooden mosaic flooring.
- As a bonding agent for plastering difficult substrates such as glazed tiles.
- For fixing insulation boards, expanded polystyrene and cork slabs.
- As a curing agent for concrete.

CHARACTERISTICS / ADVANTAGES

- Forms an impervious water and water vapour barrier on most surfaces.
- Internal or external use.
- May also be used as an adhesive or bonding aid.
- Low hazard - water clean up.
- Low odour once cured.

APPROVALS / STANDARDS

Conforms to Clause 2004:4 Specification for Highway Works.

PRODUCT INFORMATION

Packaging	5 L & 25 L tins
Shelf Life	24 months from date of manufacture when stored according to manufacturers instructions.
Storage Conditions	Store in original container in cool (+5 °C to +25 °C), dry conditions. PROTECT FROM FROST
Colour	Dries Black
Density	ca. 1.0 g/cm ³ @ +20 °C
Service Temperature	-10 °C to +85 °C.
Chemical Resistance	Resistant to: most salt solutions, dilute acids and alkalis, water.

APPLICATION INFORMATION

Yield	6 – 10 m ² / 5 L tin as approximation
Ambient Air Temperature	+5 °C to +50 °C. Do not apply below +5 °C
Drying time	4 -6 hours depending on drying conditions

VALUE BASE

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LIMITATIONS

- Do not apply when rain is imminent.
- Protect from rain and frost until cured (the coating may be assumed to be dry when rubbing with a wet finger does not produce a brown stain).
- Do not use in areas where subsequent solvent contact is likely.
- Allow sufficient drying time between coats.
- Stir well before use.
- The product may bleed through any paints subsequently applied over it. Apply a primer recommended by the paint manufacturer before overpainting.
- This product will not provide a replacement for a DPC. Ideally, it should be used in conjunction with one.
- Gloss paints and other oil or alkyd based paints must not be used directly over a surface treated with EVERBUILD® BLACK JACK® 908 D.P.M.

ECOLOGY, HEALTH AND SAFETY

Consult MSDS for full list of hazards.

APPLICATION INSTRUCTIONS

SUBSTRATE PREPARATION

STIR WELL BEFORE USE. The product is brown in colour but dries black. Before applying, ensure all surfaces are clean, touch dry (free from excess water), sound and free from any contaminants, which may affect adhesion. Base concrete must be finished off with a wooden float to give a smooth surface. Tamped surfaces are not suitable owing to the difficulty of ensuring adequate coating over the high spots. Prime porous surfaces with EVERBUILD® BLACK JACK® 908 D.P.M. diluted 1:6 with tempered (+10 °C) water and allow to dry. All phases of the installation should comply with BS Code of Practice 102: 1973 - protection of Buildings from the Ground/Section 3. Please note that EVERBUILD® BLACK JACK® 908 D.P.M. must only be diluted with lukewarm to warm water, cold water may cause the product to harden.

APPLICATION

DAMP-PROOFING FLOORS

Apply by brush, a minimum of 2 coats, each at 0.8 L/m

2, carrying the treatment up the walls to join the existing wall DPC. Allow the first coat to dry before applying the second coat at right angles to the first. When dry, a sand/cement or concrete screed of approximately 50 mm thick is then laid over the EVERBUILD® BLACK JACK® 908 D.P.M. membrane.

WATERPROOFING WALLS

If a condition of rising damp exists, the best form of treatment is the insertion of a damp proof course. Where dampness is due to penetration of the wall, proceed as follows:

a/ Exterior walls:

Level uneven surfaces with cement mortar. Apply three coats of EVERBUILD® BLACK JACK® 908 D.P.M. with a soft bristle brush, each at a rate of 0.5 L/m², allowing each coat to dry before applying the next. Allow the final coat to become tacky, then blind with clean, sharp sand.

b/ Interior walls. (moderately damp)

Remove wallpaper, loose emulsion/gloss paint and any dust or grease. Make good any damaged or perished plaster. Lightly dampen the prepared surface and apply 3 coats of EVERBUILD® BLACK JACK® 908 D.P.M. with a soft bristle brush, each at a rate of 0.5 L/m², allowing each coat to dry before applying the next. A horizontal strip running 300 mm deep should be left uncoated at the top running the whole length of the wall. This permits trapped moisture to escape by evaporation.

c/ Interior walls (very damp)

Wherever possible, very damp walls should receive an external treatment such as waterproof render/masonry paint etc. If this is not possible, the following procedure may benefit - although it must be emphasised that only adequate external treatment will cure the most severe conditions.

Hack away old plaster from the entire area. Damage to joints or brickwork must be made good with cement mortar. When the mortar has dried, apply 3 coats of EVERBUILD® BLACK JACK® 908 D.P.M. with a soft bristle brush, each at a rate of 0.5 L/m², allowing each coat to dry before applying the next. When the final coat has thoroughly dried, the wall should be replastered.

DECORATING

Gloss paints and other oil or alkyd based paints must not be used over a surface treated with EVERBUILD® BLACK JACK® 908 D.P.M.

Where EVERBUILD® BLACK JACK® 908 D.P.M. has been used over plaster, it is recommended that a lining paper, fixed with cellulose paste should be hung. This will provide a suitable surface for emulsion paints and for wallpapering.

NOTE: Vinyl coated papers or paper backed vinyls

should NOT be hung over EVERBUILD® BLACK JACK® 908 D.P.M.

WATERPROOFING STRUCTURES

EVERBUILD® BLACK JACK® 908 D.P.M. will provide a waterproof membrane on bridge abutments, retaining walls, culverts, concrete or brick foundations. It also acts as a curing membrane when applied to green concrete.

The surface should be sound and free from dust, dirt and grease. Hot, very dry or absorbent surfaces should be dampened with water. Apply two coats of EVERBUILD® BLACK JACK® 908 D.P.M. each at a rate of 0.5 L/m².

FIXING WOOD BLOCKS AND MOSAICS

For fixing wood blocks of 12 mm thickness and above, dip the bottom face of each block into the material and place into position immediately. Coverage is approximately 1.1 L/m².

For fixing wood mosaic panels, spread EVERBUILD® BLACK JACK® 908 D.P.M. onto the surface at 0.8 L/m² and place the panels into position immediately. A minimum of 24 hours should be allowed before sanding/trafficking.

Where under floor heating is incorporated into the sub floor the heating must be turned off for at least 48 hours before, and until after, tiling.

NOTE: On low porosity or non-porous surfaces, allow EVERBUILD® BLACK JACK® 908 D.P.M. to partially dry before placing the wood mosaics/blocks into position. In most circumstances a period of 30-40 mins will suffice, but do not allow to dry off completely. Under no circumstances, should such floorings be laid on existing floor coverings.

PLASTER/RENDER BONDING/KEYING

When a "keyed" surface is required (plastering onto glazed tiles, gloss painted walls and bricks, or to bond sand/cement renders) apply two coats of EVERBUILD® BLACK JACK® 908 D.P.M. each at a minimum rate of 0.25 L/m². Allow the first coat to dry before applying the second, and blind the second coat with clean sharp, dry, sand. Allow at least 48 hours before plastering or rendering (at least 6 mm thickness).

NOTE if gloss or alkyd paints are to be used as a decorative finish, the plaster over the EVERBUILD® BLACK JACK® 908 D.P.M. must be applied in two coats to give a minimum total thickness of 15 mm.

FIXING INSULATION BOARD, EXPANDED POLYSTYRENE AND CORK SLABS.

Surfaces should be clean, level and free from dust or loose matter. A coat should be applied to the porous base and the insulation material placed whilst the EVERBUILD® BLACK JACK® 908 D.P.M. is still wet. If necessary, the boards should be supported until the EVERBUILD® BLACK JACK® 908 D.P.M. has set.

CLEANING OF TOOLS

Clean tools immediately after use with water. Once cured, dried product can be removed with Kerosene (paraffin) or white spirit.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA LIMITED

Watchmead
Welwyn Garden City
Hertfordshire, AL7 1BQ
Tel: 01707 394444
Web: www.sika.co.uk
Twitter: @SikaLimited

Product Data Sheet

EVERBUILD® BLACK
JACK® 908 D.P.M.
September 2023,
Version 02.01
020915792000000016
3/3



BUILDING TRUST



EVERBUILDBLACKJACK908DPM-en-GBEVER-(09-2023)-2-1.pdf