



# **Aquafix**

Revision: 9/10/2019 Page 1 from 1

#### **Technical data**

Basis	styrene acrylate	
Consistency	Paste	
Curing system	Physical drying	
Skin formation* (23°C/50% R.H.)	Ca. 10 min	
Density	Ca. 0,95 g/ml	
Maximum allowed distortion	10 %	
Temperature resistance**	-20 °C → 90 °C	
Application temperature	$5  ^{\circ}\text{C} \rightarrow 30  ^{\circ}\text{C}$	
Shrinkage	Ca. 20%	

<sup>\*</sup> These values may vary depending on environmental factors such as temperature, moisture, and type of substrates. \*\* This information relates to fully cured product.

# **Product description**

Aquafix is a plasto-elastic, one-component sealant based on copolymers.

#### **Properties**

- Totally transparent, crystal clear
- Very easy to apply
- Solvent based
- Good adhesion to many substrates
- Can be painted over after curing
- UV resistant, waterproof and resistant to weathering

# **Applications**

- Repair product for leaks in gutters, drainpipes.
- Implementing emergency repairs, even in rain
- Sealant at cracks and seams.

#### **Packaging**

Colour: transparent Packaging: 310 ml cartridge

#### Shelf life

At least 12 months in unopened packaging in a dry storage place at temperatures between +5 °C and +25 °C.

## **Substrates**

Substrates: all usual building substrates Nature: clean, free of dust and grease, can be moist. Surface preparation: No pretreatment required. A preliminary adhesion test on every surface is recommended.

### Application method

Application method: With manual- or pneumatic caulking gun. Finish with a spatula or putty knife.

Cleaning: Clean with White Spirit or Soudal Surface Cleaner immediately after use (before curing).

Finishing: With a soapy solution or Soudal Finishing Solution before skinning.

Repair: With the same material.

## **Health- and Safety Recommendations**

Take the usual labour hygiene into account. Consult the packaging label for more information.

Remark: This technical data sheet replaces al previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.

 Soudal NV
 Everdongenlaan 18 - 20
 B-2300 Turnhout, Belgium

 Tel: +32 (0)14-42.42.31
 Fax: +32 (0)14-42.65.14
 www.soudal.com