



Genius Gun Insulation Foam

Revisie datum: 27/01/2017 Pagina 1 van 2

Technical Data:

Base	Polyurethane
Consistency	Stable Foam (does not sag)
Curing System	Moisture Cure
Skin Formation (20°C at 60% R.H.)	Ca 8 min.
Drying time	Ca 90min – 30mm foam bead (20°C/65% R.H.)
Foam Yield (FEICA OCF TM 1003)	600 ml yields 20 l cured foam
Shrink	<3%
Postexpansion	None
Cellular Structure	Ca 70-80% closed cells
Specific Gravity	Ca. 26kg/m³ (extruded, fully cured)
Temperature Resistance	-40°C until +90°C when cured Short term (up to 1 hour) 120°C
Kleur	Champagne
Fire Class	B3 (DIN4102 part2)
Water Absorption	1% Vol. (DIN53422)
Accoustic Rating (EN ISO 717-1)	60 dB
Insulation Factor	35mW/meter Kelvin (DIN 52612)
Pressure Strength (DIN 53421)	Ca. 3 N/cm ²
Bowing Strength (DIN 53423)	Ca. 7 N/cm²
Shear Strength (DIN 53427)	Ca. 17 N/cm ²



Product:

Genius Gun Insulation Foam is a ready to use single component self expanding Polyurethane Foam. Due to the the patented Genius Gun system the application of PU Foam becomes very easy and precise. The extrusion straw can be resealed which makes it possible to continue the application from a partially used canister for several weeks.

Characteristics:

- post expansion
- **Excellent filling characteristics**
- Excellent adhesion to all building materials (except PE, PP and PTFE)
- High insulation values, both thermal and acoustical
- Excellent installation performance

Excellent form stability - no shrink, no Packaging:

Aerosol canister of 600mL (net content)

Installation of door- and windowframes

Sealing and filling of openings and

Creation of a sound deadening layer

All other usual PU Foam applications

Improvement of insulation in cold store

cavities in roof constructions

Creation of an acoustic screen

Applications:

facilities

Filling of cavities

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability





Genius Gun Insulation Foam

Revisie datum: 27/01/2017 Pagina 2 van 2

Shelf Life:

- 12 months in unopened packaging in a cool and dry storage place at temperatures between +5°C and +25°.
- Always store can with the valve pointed upwards

Application Instructions:

Shake the canister thoroughly for ca 30 seconds. Open the lid on the top and wear the enclosed gloves. Straighten the applicator

Apply a fine water spray to the surface which needs to be clean and free of grease and

Turn around the canister and extrude the foam carefully by applying pressure on the trigger. Fill cavities on for 30 to 40 % as the foam will continue to expand during the curing process. Shake canister regularly durina application. If Foam is applied in several layers, moisten between each layer of foam. At the end of the application, close the applicator tube with the sealing plug and click into the holder. Close the lid. The canister can be reactivated for up to 6 weeks if resealed

Uncured foam can be removed with Foam Cleaner or acetone. Cured foam can only be removed mechanically.

Application temperature: +5°C to +30°C.

Health- and Safety Recommendation:

- Apply the usual industrial hygiene.
- Wear gloves and safety goggles.
- Remove cured foam by mechnical means only, never burn away

Remarks:

- Always moisten surfaces in order to improve curing and cellular structure
- Cured PU foam must be protected from UV-radiation by painting or applying a top layer of sealants (silicone, MS Polymer,
- For the filling of large volumes apply product in layers and moisten between each layer
- We recommend preliminary compatibility tests on surfaces on which PU Foams have not been applied previously.
- Always store canister with the valve pointed upwards

VOORBEREIDING / PRÉPARATION











GEBRUIK / UTILISATION





Preparation: 1: shake 30 seconds 2: open lid 3: wear gloves and safety goggles Use: 4: Straighten applicator tube 5: turn canister and press the trigger Storage after use: 6: remove sealing plug 7: seal applicator tube with the sealing plug and close the lid

Remark: This technical data sheet replaces al previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability

Soudal (UK) Limited Unit A, Tame Park, Vanguard Tel: +44 1827-261.092 Fax: +44 1827-284.454

UK-Tamworth B77 5DY www.soudal.com