

PRODUCT DATA SHEET

EVERBUILD® BLACK JACK® 905 ALL WEATHER ROOF COATING

SOLVENT BASED, FULL-BODIED BITUMEN COMPOUND WITH ADDED FIBRES FOR REINFORCEMENT

PRODUCT DESCRIPTION

EVERBUILD® BLACK JACK® 905 ALL WEATHER ROOF COATING is a solvent based, full-bodied, black, brushable bitumen compound with added fibres for reinforcement. It is an effective general purpose roof coating that is resistant to wash-off by rain almost immediately, and is therefore ideally suited for winter use. The product is specifically designed for general waterproofing in all roofing applications, guttering (non plastic) and structural steelwork. Dries to a tough black coating.

USES

EVERBUILD® BLACK JACK® 905 ALL WEATHER ROOF COATING may be applied by brush to waterproof and re-seal many different types of roof coverings, including:

1. Asphalt roofs.
2. Built-up felt roofs.
3. Concrete roof decks.
4. Asbestos-Cement sheeting.
5. Metal sheeting, including iron, steel, zinc and lead.
6. Slates, tiles.

EVERBUILD® BLACK JACK® 905 ALL WEATHER ROOF COATING may be used in conjunction with a rot-proof hessian reinforcement scrim or bitumen coated glass fibre scrim such as a glass membrane.

EVERBUILD® BLACK JACK® 905 ALL WEATHER ROOF COATING may also be used as a vapour barrier on walls and roofs.

CHARACTERISTICS / ADVANTAGES

- Fast drying.
- Fibre-reinforced.
- Weatherproof.
- Unaffected by water immediately after application - can be applied when rain is imminent.
- Can also be used to bond felt.
- Brush applied.

Type Of Solvent	White spirit
Application Temperature	5°C to 30°C. Surfaces must be free from ice and water
Heat Flow Resistance	The cured film will not sag or flow under normal conditions

PRODUCT INFORMATION

Packaging	5L & 25L tins
Colour	Black

Shelf Life	Storage life 24 months in tightly sealed undamaged containers.
Storage Conditions	EVERBUILD® BLACK JACK® 905 ALL WEATHER ROOF COATING contains a flammable solvent, and all normal precautions against fire must be taken during both storage and use. Store in original container in cool (5°C - 25°C) dry conditions. Keep away from sources of ignition.
Density	ca. 1.0 g/cm ³ at 20°C
Reaction to Fire	Wet product is flammable, dry film will burn
Chemical Resistance	Resistant to: most salt solutions, dilute acids and alkalis, water. Not resistant to: oils, solvents and some detergent solutions/glass cleaning solutions.
Service Temperature	-10°C to +85°C

APPLICATION INFORMATION

Yield	1.25m ² per litre per coat depending on porosity of substrate. Two coats should give a dried film of approximately 0.9mm.
Drying time	24 hours depending on drying conditions. Allow 24 hours between coats.

APPLICATION INSTRUCTIONS

SUBSTRATE PREPARATION

No roof coating product can be expected to repair an existing roof that is not structurally sound and stable. Before using a surface coating the roof structure should be inspected and, if necessary, put in order. All cracked, broken, slipped or missing slates, tiles, sheets or other forms of covering should be replaced or re-fixed, and cracks in felt or asphalt filled. **Safety recommendation: do not coat roof lights, windows, glass or translucent sheets. These will constitute a hidden hazard if disguised.**

Preparation of the surface is of great importance and will influence the degree of adhesion and life of the renovation. All roof surfaces to be coated should be sound, stable and clean, i.e. free from loose debris, dirt, dust and grease. All traces of algae and fungal growth should be removed using a stiff bristle brush. Where algae and fungi have been present, remove them completely and treat the surface with EVERBUILD® FUNGICIDAL WASH to kill any remaining spores, thereby discouraging return of growth.

APPLICATION

Note: These instructions follow the recommendations of the National Federation of Roofing Contractors Code of Practice governing the use of Liquid Coatings for Roof Waterproofing.

ASPHALT ROOFS

On asphalt roofs where blisters have occurred, these should be heated with a blow lamp until soft and then smoothed out. If the asphalt is crumbling or badly cracked it must be removed and replaced with a polyester based underlay and bonded to the roof deck. EVERBUILD® BLACK JACK® 905 ALL WEATHER ROOF COATING should be applied by brush in 2 coats, the first being allowed to dry before the second is applied.

BUILT-UP FELT ROOFS

Remove any loose chippings and carry out the preparatory work detailed above. Minor marks and defects

will be effectively filled and covered by EVERBUILD® BLACK JACK® 905 ALL WEATHER ROOF COATING, but where these are wider than 0.75mm they should first be filled with BLACK JACK® BITUMEN MASTIC and the mastic allowed to dry.

Blisters in roofing felt should be opened out, cleaned with a stiff bristle brush and coated with EVERBUILD® BLACK JACK® 905 ALL WEATHER ROOF COATING at 1.50 square metres per litre. This coating should be allowed to set until it is "tacky" and then the felt should be re-fixed by bonding it down.

In each case, further coats of EVERBUILD® BLACK JACK® 905 ALL WEATHER ROOF COATING and a glass membrane should then be applied

REINFORCED CONCRETE

Carry out preparatory work. New decks should first be allowed to cure and then primed using BLACK JACK® BITUMEN AND FLASHING PRIMER at 4-6 square metres per litre (rate depending upon porosity).

LIGHTWEIGHT CONCRETE

Carry out preparatory work. Allow the concrete roof deck and topping screed to cure. A glass fibre felt underlay should be partially bonded to the surface using BLACK JACK® ROOF FELT ADHESIVE. The felt should be lapped, sealed and adequate ventilation provided for the materials beneath it. EVERBUILD® BLACK JACK® 905 ALL WEATHER ROOF COATING and a glass membrane should then be applied.

ASBESTOS-CEMENT SHEETING

Carry out preparatory work. It is particularly important to ensure that the Asbestos-Cement is not saturated with water before protective coating commences. Wait until the Asbestos-Cement sheeting is dry and then apply two coats of EVERBUILD® BLACK JACK® 905 ALL WEATHER ROOF COATING, each at 1m² per litre, allowing the first coat to dry before application of the second.

METAL SURFACES

Where these show signs of corrosion such as loose rust this should be removed by abrading with a metal-bristled brush. A rust inhibitive treatment such as Zinc Phosphate Primer should be applied to ensure that the rust does not return. In normal circumstances, abrading with a brush is usually sufficient preparation. EVERBUILD® BLACK JACK® 905 ALL WEATHER ROOF COATING should be applied in 2 coats at 1.5 square metres per litre per coat.

SLATES AND TILES

Carry out preparatory work. The roof should be examined for damaged or loose slates or tiles. Any loose slates or sheets should be re-fixed firmly in place.

EVERBUILD® BLACK JACK® 905 ALL WEATHER ROOF COATING and a glass membrane should then be applied.

ALL-WEATHER ROOF COATING AND SCRIM TREATMENTS

In order to bridge gaps, cracks and fissures and in all cases where roof surfaces are in advanced states of decay, it is recommended that EVERBUILD® BLACK JACK® 905 ALL WEATHER ROOF COATING be used in conjunction with a reinforcing membrane, either rot-proof hessian or, preferably, a glass membrane. Having ensured that the surface is clean and receptive to the coating product, apply a first coat at one square metre per litre. Immediately apply the glass membrane into wet EVERBUILD® BLACK JACK® 905 ALL WEATHER ROOF COATING film, using a brush charged with further EVERBUILD® BLACK JACK® 905 ALL WEATHER ROOF COATING. Ensure that complete contact is achieved and that no air is trapped beneath the membrane.

The glass membrane should be lapped by 50 to 75mm and the inside of each lap should be painted with EVERBUILD® BLACK JACK® 905 ALL WEATHER ROOF COATING. Small gaps and differences in levels should be bridged ensuring that the glass membrane is not pulled too tightly across the gap so that any movement in the structure will be accommodated.

At walls and parapets, continue the glass membrane and EVERBUILD® BLACK JACK® 905 ALL WEATHER ROOF COATING sandwich vertically for at least 150mm and secure using self-adhesive flashing (150mm width) allowing 75mm to be in contact with the brickwork above. Apply a second coat of EVERBUILD® BLACK JACK® 905 ALL WEATHER ROOF COATING and allow this to dry.

FINAL SURFACE

It is beneficial to the coating, and to the rest of the roof structure, to give a final solar reflective finish using BLACK JACK® SOLAR REFLECTIVE PAINT. An exposed black bituminous surface should be avoided on a pitched or flat roof. When using EVERBUILD® BLACK JACK® 905 ALL WEATHER ROOF COATING a third and final coat should be preferably applied at 1.5 square metres per litre and, while the film is still “tacky”, well blinded with 1 to 20mm (7 to 14 mesh) stone chip-pings or clean sharp sand. Alternatively, wait for a minimum of 3 days, preferably 2 weeks, then apply a solar reflective coating using BLACK JACK® SOLAR REFLECTIVE PAINT.

VAPOUR BARRIER

When insulating material is placed on a flat roof deck it is essential to prevent condensation water vapour from entering the insulation. If this is allowed to happen it can damage the insulation. Two coats of EVERBUILD® BLACK JACK® 905 ALL WEATHER ROOF COATING, the first applied at one square metre per litre, the second at 1.5 square metres per litre, will help prevent this. EVERBUILD® BLACK JACK® 905 ALL WEATHER ROOF COATING should be applied to the “warm side”, with care being taken to avoid pin holes and imperfections in the coating. When dry, the insulation may be applied over it.

LIMITATIONS

- Do not apply to damp or wet areas. Use BLACK JACK® ROOFING EMULSION instead.
- Do not use in areas where subsequent solvent contact is likely.
- Do not use in silage pits
- Avoid inhalation of vapours in confined spaces.
- Allow sufficient drying time between coats.
- The product may bleed through any paints subsequently applied over it. Apply a primer recommended by the paint manufacturer before overpainting.

VALUE BASE

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

ECOLOGY, HEALTH AND SAFETY

Consult MSDS for full list of hazards.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our

current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

EVERBUILD BUILDING PRODUCTS LTD

Site 41, Knowsthorpe Way
Cross Green Industrial Estate
Leeds, LS9 0SW
Tel: 0113 240 3456
Web: www.everbuild.co.uk
Twitter: @everbuild

SIKA LIMITED

Watchmead
Welwyn Garden City
Hertfordshire, AL7 1BQ
Tel: 01707 394444
Web: www.sika.co.uk
Twitter: @SikaLimited

SIKA IRELAND LIMITED

Ballymun Industrial Estate
Ballymun
Dublin 11, Ireland
Tel: +353 1 862 0709
Web: www.sika.ie
Twitter: @SikaIreland

EVERBUILDBLACKJACK905ALLWEATHERROOFCOATING-en-GBEVER-(05-2018)-1-1.pdf

Product Data Sheet
EVERBUILD® BLACK JACK® 905 ALL WEATHER ROOF
May 2018, Version 01.01
020920049000000005